

Product Data Sheet Hydro Turf® CS w/40 mil MicroSpike®



GEOMEMBRANE COMPONENT	Test Method	HDPE Values
Thickness (nominal), mil (mm)	ASTM D5994	40 (1.02)
Thickness (min. avg.), mil (mm)	ASTM D5994	38 (0.95)
Thickness (8 out of 10), mil (mm)	ASTM D5994	36 (0.90)
Thickness (lowest indiv.), mil (mm)	ASTM D5994	34 (0.85)
Asperity Height (min. avg.), mil. (mm)	ASTM D7466	20 (0.51)
Density, g/cc	ASTM D792, Method B	0.94 (min.)
Tensile Properties (avg. both directions)	ASTM D6693, Type IV	
Strength @Yield (min. avg.), lb/in. width	ASTM D6693, Type IV	88 (15.4)
Elongation @ Yield (min. avg.), % (GL=1.3 in.)	ASTM D6693, Type IV	13
Strength@Break (min. avg.), lb./in. width	ASTM D6693, Type IV	88 (15.4)
Elongation@Break (min. avg.), lbs. %(GL=2.0	ASTM D6693, Type IV	350
Tear Resistance (min. avg.), lbs. (N)	ASTM D1004	30 (133)
Puncture Resistance (min. avg.) lbs. (N)	ASTM D4833	90 (400)
Carbon Black Content (range %)	ASTM D 4218	2-3
Carbon Black Dispersion (Category)	ASTM D5596	Only near spherical agglomerates for 10 views in Cat. 1 or 2
Stress Crack Resistance (Single Point NCTL),	ASTM D5397, Appendix	500
Oxidative Induction Time, minutes	ASTM D3895, 200°C, 1 atm	≥140

Agri America's geomembranes are certified to pass Low Temp. Brittleness via. ASTM D746 (-80°C), and Dimensional Stability via. ASTM D1204 (± 2% @ 100°C)

ENGINEERED TURF COMPONENT	Test Method	Turf Type 1	Turf Type 2
Yarn	ASTM D1577	Polyethylene Fibrillated Tape	Polyethylene Monofilament
Tensile Strength of Yarn	ASTM D2256	15 lbs. min.	15 lbs. min.
Tufted Pile Height	ASTM D5823	1.25 ± 0.25 Inches	2.25 ± 0.25 Inches
Pile Weight	ASTM D5848	19 ± 2 oz. yd ²	34 ± 2 oz. yd ²
CBR Puncture	ASTM D6241	800 lb. (MARV)	800 lb. (MARV)
Tensile Product (MD/XD)	ASTM D4595	1,000 lb./ft. min. (MARV)	1,000 lb./ft. min. (MARV)
Aerodynamic Evaluation	GTRI Wind Tunnel	120 mph with max. uplift of 0.12 lb/sf	120 mph with max. uplift of 0.12 lb/sf
Engineered Turf Fiber UV Stability	ASTM G147	>60% retained tensile strength at 100 yrs. (projected)	>60% retained tensile strength at 100 yrs. (projected)
Steady State Hydraulic Overtopping	ASTM D7277/D7276	40 ft/s velocity	40 ft/s velocity
Manning's 'n' Value	ASTM D7277/D7276	0.017 to 0.020	0.018 to 0.025
Internal Friction of Combined Components (Low Confining Stress)	ASTM D5321	23°, min. (peak)	23°, min. (peak)
HydroBinder® Infill Mix	ASTM C387/ASTMC109	3/4 inch Thick Infill 5000psi (min. at 28 days)	3/4 inch Thick Infill 5000psi (min. at 28 days)

SUPPLY INFORMATION (Standard Roll Dimensions)

	Thickness		Width			Length		Area (approx.)		Weight (avg.)	
	mil	mm	ft.	m	ft.	m	ft ²	m ²	lbs	kg	
MicroSpike® Geomembrane	40	1.02	23	7	750	229	17,250	1603	~3900	~1770	
Turf Type 1 Component	N/A	N/A	15	4.6	300	91.4	4,500	418	~840	~380	
Turf Type 2 Component	N/A	N/A	12	3.6	300	91.4	3,600	335	~1000	~454	

ClosureTurf®, HydroTurf®, VersaCap® and HydroBinder® products are U.S. registered trademarks that designate products by Watershed Geosynthetics, LLC. These products are the subjects of issued U.S. and foreign patents and/or pending U.S. and foreign patent applications.